

ITEM: LUCIDO

SIZE: 8x25

SERIES: VIBES

| PHYSICAL PROPERTIES                                                                                                    | ISO13006 Group Bla - Requirements                                          | VALUE                                                                                            |
|------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------|
| ISO 10545/3 WATER ABSORPTION<br>(%)                                                                                    | average value $\leq 0,5$<br>single value $\leq 0,6$                        | 0,08<br>0,09                                                                                     |
| ISO 10545/4 MODULUS OF RUPTURE<br>(N/mm <sup>2</sup> )                                                                 | average value $\geq 35$<br>single value $\geq 32$                          | 38,88<br>37,09                                                                                   |
| ISO 10545/4 BREAKING STRENGHT<br>(N)                                                                                   | $\geq 700$ (thickness < 7,5 mm )<br>$\geq 1300$ (thickness $\geq 7,5$ mm ) | 1712                                                                                             |
| ISO 10545/6 RESISTANCE TO DEEP<br>ABRASION<br>mm <sup>3</sup>                                                          | 175 max                                                                    | 118                                                                                              |
| ISO 10545/8 COEFFICIENT OF LINEAR<br>THERMAL EXPANSION from 20°C to 100<br>°C<br>(10 <sup>-6</sup> .°C <sup>-1</sup> ) | TEST METHOD AVAILABLE                                                      | 6,23                                                                                             |
| ISO 10545/14 RESISTANCE TO STAINS<br>CLASS from 1 to 5                                                                 | $\geq 3$                                                                   | Chrome green in light oil 5<br>Iodine, alcoholic solution 5<br>Olive oil 5                       |
| ISO 10545/13 RESISTANCE HOUSEHOLD<br>CHEMICALS<br>AND SWIMMING POOL SALTS<br>CLASS GA - GB - GC                        | min. GB                                                                    | 1day Amm. Chlor. 100g/l GB<br>1day Hypochl. Sodi. 20mg/l GB                                      |
| ISO 10545/13 RESISTANCE TO ACIDS<br>AND ALKALIS (low concentrations)<br>CLASS GLA - GLB - GLC                          | Manufacturer to state classification                                       | 4days Hydrochloric acid 3% GLB<br>1day Citric acid 100g/l GLB<br>4days Potass. hydrox. 30g/l GLB |
| RESISTANCE TO SOILS (internal test)<br>CLASS from 1 to 4 *                                                             |                                                                            | 2                                                                                                |

Signature: Davide Gilli